



### IREFGUN 22

<b>Max. Temperature Service:</b>	1200 °C
<b>Classification:</b>	Light weight Gunning mix.
<b>Main Raw Material Component:</b>	Blended gunable employing calcined clays , firm lightweight aggregates & calcium – aluminate binder
<b>Type Of Bond:</b>	Hydraulic
<b>Grain Size</b>	0 – 3.5 mm
<b>Water required For Pouring</b>	44 – 53 %
<b>Features and Main Applications:</b>	Low Thermal Conductivity. Good refractoriness, Good strength, Excellent resistance to thermal shock, easily installed by gunning or troweling. Recommended for Chemical & Petrochemical Industries, Various industrial furnaces , boilers , incinerators , stacks and as backup for other refractories suitable for greater mechanical abuse and higher temperatures.

<b>Chemical Composition</b> (Calcined base)			
<b>Al<sub>2</sub>O<sub>3</sub> %</b>	<b>SiO<sub>2</sub> %</b>	<b>Fe<sub>2</sub>O<sub>3</sub> %</b>	<b>CaO %</b>
31 – 37	37 – 42	4.5 – 7.5	12 – 16

<b>Thermomechanical Properties</b>		
<i>After drying at 110 °C</i>		
<b>Bulk Density</b>	(Kg/m <sup>3</sup> )	< 1100
<b>Cold Crushing Strength</b>	( kg/cm <sup>2</sup> )	> 20
<b>Linear Change</b>	( %)	Negligible

All data based on cast specimens . ASTM procedures , where applicable , used for determination of data .

For data of vibration cast or gunned , consult our sales & Engineering service's experts .

All data subject to reasonable deviations , and therefore , should not be used for specification purposes .ASTM Test Methods, where applicable, used for determination of data.

Revision:2

Date of issue: 1397/09/05

Code: IRF-ST-Q-860-19

Revision:00